

Tampapol TPY



Pad printing ink for ABS, rigid PVC, pre-treated polyethylene and polypropylene, varnished surfaces, thermosetting plastics, and metal

Glossy, good opacity, fast drying 1- or 2- component ink system, resistant to chemicals

Vers. 2
2003
19 Apr

Field of Application

Substrates

Tampapol TPY is extremely well suited to print onto ABS, rigid PVC, pre-treated polyethylene (PE) and polypropylene (PP), thermosetting plastics, metal, varnished surfaces, wood, paper, and cardboard. By adding Hardener H 1 or H 2, Tampapol TPY achieves increased resistance and adhesion characteristics.

When printing onto polyethylene or polypropylene, please make sure to pre-treat the surface of your substrate by flaming or Corona discharge as usual.

As per our experience, you can achieve a very good adhesion with the Tampapol TPY with a surface tension of at least 42-48 mN/m. On polypropylene, you can also apply a thin film of our colourless Primer P 2 for surface pre-treatment (see technical data sheet "Primer P 2").

For multiple colour printing, please consider that you should not flame the substrate between print sequences, as this may reduce intercoat adhesion.

Since all the print substrates mentioned may be different in printability even within an individual type, preliminary trials are essential to determine the suitability for the intended use.

Field of use

Tampapol TPY is mainly used to print onto packaging made of polyethylene, polypropylene or rigid PVC.

Characteristics

Pot life

The pot life (processing period) at room temperature (approx. 20 °C) will be about 12-14 h with H 1 and about 8-10 h with H 2. Higher temperatures reduce pot life.

If the mentioned times are exceeded, the ink's adhesion and resistance may be reduced, even if the ink characteristics show no noticeable change.

Drying

Physically fast drying. Touch-dry at 20°C after approx. 2 min, at 30°C after approx. 30-40 sec. The addition of Hardener H 1 or H 2 will extend the drying time.

The times mentioned above vary according to substrate, depth of cliché, drying conditions, and the auxiliaries used.

Parallel to physical drying (i.e. to the evaporation of the solvents used), the actual hardening of the ink film is caused by the chemical cross-linking reaction between ink and hardener. Chemical crosslinking can be accelerated by higher temperatures.

The processing and curing temperature should not be lower than 15 °C as irreversible damage can occur. Also avoid high humidity for several hours after printing as the hardener is sensitive to humidity.

Tampapol TPY



Fade resistance

Only pigments of high fade resistance are used in the Tampapol TPY range.

Shades mixed by adding overprint varnish or other colour shades, and especially white, have a reduced fade and weather resistance depending on their mixing ratio. The fade resistance also decreases if the printed ink film thickness is reduced.

The pigments used are resistant to solvents and plasticizers.

Stress Resistance

After proper and thorough drying, the ink film exhibits outstanding adhesion as well as rub, scratch, and block resistance and is resistant to oils, greases, water diluted acids and alkalines, and alcohol.

In some cases surface stability as well as adhesion and resistance to solvents may be improved by adding 10 % of Hardener H 1 or H 2.

Range

Refer to the shade card "System Tampacolor"

TPY 920	Lemon	TPY 950	Violet*
TPY 922	Light Yellow *	TPY 952	Ultramarine Blue*
TPY 924	Medium Yellow	TPY 954	Medium Blue
TPY 926	Orange	TPY 956	Brilliant Blue*
TPY 930	Vermilion *	TPY 960	Blue Green
TPY 932	Scarlet Red	TPY 962	Grass Green *
TPY 934	Carmine Red	TPY 970	White
TPY 936	Magenta*	TPY 980	Black
TPY 940	Brown		

*semi-transparent/transparent

All shades are intermixable. To maintain the special characteristics of this outstanding ink range, the TPY should not be mixed with other ink types.

Tampapol TPY is included in our computerised colour matching system Marabu-mix.

By using these basic shades in accordance with the mixing ratios provided by the Marabu-Color-Manager software, it is possible to produce shades of the popular colour reference systems PANTONE®, HKS®, RAL®, and Marabu System 21.

Further shades available

TPY 470 Rotary White, matt

Shades for 4-colour process prints

TPY 429 Process Yellow (Yellow)

TPY 439 Process Red (Magenta)

TPY 459 Process Blue (Cyan)

TPY 489 Process Black (Black)

Press-ready gold and silver shades

TPY 191 Silver

TPY 192 Rich Pale Gold

TPY 193 Rich Gold

Clears

TPY 910 Overprint Varnish, can also be used as bronze binder

Bronzes

(to be mixed with Overprint Varnish TPY 910)

S 181 Aluminium

S 182 Rich Pale Gold

S 183 Rich Gold

S 184 Pale Gold

S 186 Copper

S 190 Aluminium, rub-resistant

Due to their chemical structure, Pale Gold and Copper have a reduced processing time. Please prepare mixtures daily, as they cannot be stored and must be processed within 8 h.

For the processing of metallics, we refer you to our separate data sheet "Bronze Inks".

The pigments used in the above mentioned standard shades, based on their chemical structure, correspond to the EEC regulations EN 71/part 3, safety of toys - migration of specific elements. All colours are suited for printing onto toys.

Tampapol TPY



Auxiliaries

Thinner:	TPV TPV 2, fast thinner TPV 3, slow thinner
Hardener:	H 1 H 2, fast hardener HT 1, heat-reactive
Mixing ratio:	10 p. ink : 1 p. hardener
Retarder:	SV 1 VP, Retarder Paste
Matting product:	ABM, Matting Paste MP, Matting Powder
Antistatic Paste:	AP
Opaquing Paste:	OP 170
Primer:	P 2, for polypropylene
Cleaner:	UR 3
Printing Modifier:	ES, addition: 0 - max. 1 %

To adjust printing viscosity, it is generally sufficient to add 10 - 20 % of Thinner TPV to the ink. Thinner TPV 2 can be used for fast printing, TPV 3 for slow printing requirements.

For the printing of very fine motives, the Retarder SV 1 or Retarder Paste VP may be added to the ink. An excessive addition may result in ink transfer problems.

Attention

For an ink mixture containing retarder, only thinner should be used for additional thinning during the print run.

By adding the Opaquing Paste 170, the opacity of colour shades can significantly be increased without influencing the chemical and dry abrasion resistance considerably. Maximum quantity to be added is 15 %. OP 170 is not suitable for using it with white shades.

Printing Modifier ES contains silicone. It can be used to rectify flow problems on critical substrates by adding up to 1 % by weight to the ink.

If an excessive amount of printing modifier is added, flow problems are increased and adhesion may be reduced, especially when over-printing.

Cleaning

To clean ink containers, clichés, and tools, please use our Cleaner UR 3.

Recommendation

The ink should be stirred well before printing. To protect the ink in opened containers against excessive drying, it can be carefully covered with a layer of thinner which can then later be stirred into the ink prior to printing.

Tampapol TPY



Labelling

For our ink type Tampapol TPY and its additives and auxiliaries there are current Material Safety Data Sheets according to EC-regulation 91/155 informing in detail about all relevant safety data including labelling according to the present EEC regulations as to health and safety labelling requirements.

Such health and safety data may also be derived from the respective label.

The ink has a flash point between 21 °C and 100 °C. Since the ink is not considered as a flammable liquid due to its pastous nature, any specific regulations for the handling of flammable liquids do not apply.

Note

Please refer to the information in our technical data sheets of pad printing inks.

Our technical advice whether spoken, written, or through test trials corresponds to our current knowledge to inform about our products and their use. This is not meant as an assurance for certain properties of the products nor their suitability for each application.

You are, therefore, obliged to conduct your own tests with our supplied products to confirm their suitability for the desired process or purpose. The selection and testing of the ink for specific application is exclusively your responsibility.

Should, however, any liability claims arise, they shall be limited to the value of the goods delivered by us and utilised by you with respect to any and all damages not caused intentionally or by gross negligence.